



SPRAYnBOND FUSIBLE ADHESIVE - #4012

DIRECTIONS:


1. Pre-wash all materials without fabric softeners. Always pre-test on materials before starting project. Protect your work surface.
2. Preheat iron to high heat (polyester setting), no steam.
3. Shake well before use. Always spray back of item to be bonded.
4. Hold can upright, 8-10 inches from surface. Press nozzle and apply adhesive in short bursts using a sweeping motion to evenly coat surface, making sure to cover all edges.
5. Allow to dry. Place item, adhesive side down, on top of project.
6. Iron, using firm pressure in a circular motion, for 30 seconds on each section until entire piece is bonded. Repeat Step 6 on reverse side for an additional 15 seconds. Let cool.
7. Hold can upside down and press for a short burst to clear nozzle before storing.



Spray



Place



Iron

TIPS:

- Cover delicate fabrics with parchment paper.
- Iron thick fabrics an additional 6 seconds from the back of project.
- The thicker the application of adhesive, the stronger the bond!
- Once ironed the adhered item does not need to be sewn, but it can be sewn if so desired.



Delicate Was
Cold Water



Tumble Dry
Delicate Cycle
Low Heat